

# BEYOND FLOORS...

# **URECO MEP**

# HYBRID WATERPROOFING MEMBRANE

TDSMEPEN.V01

# PRODUCT DESCRIPTION

URECO MEP is a high quality pigmented, two components hybrid waterproofing membrane. URECO MEP is also self-priming. URECO MEP is designed to give superior adhesion in addition to providing a waterproof and seamless surface. URECO MEP is offered in different antislip texture (sold separately), smooth or with aluminum oxyde. For a complete system and maximum protection over the years, the application of a topcoat Ureco GTC is required.

#### **BENEFITS**

- Self priming
- Easy application
- Economical application
- Durable, impermeable, seamless and esthetic
- Superior Adhesion
- Good chemical and mechanical resistance
- Does not support growth of bacteria and fungus
- Easily cleaned, maintained and a more sanitary work environment
- Maintains flexibility in wide temperature ranges and over wide range of ages

# **COLORS**

# SOLID COLORS

Light Gray, Steel Gray

# **TYPICAL USES**

- Interior garage
- Multi-level parking
- Pedestrian walkway
- Mechanical room
- Structural concrete
- Balcony, garage and terraces
- Access ramps
- Bridge decks
- Sports stadium, arena
- Hospitals and schools

## **PACKAGING**

URECO MEP is available in premeasured kit of 18 liters / kit. All kits containing 5 part A of resin and 1 part B hardener.

## **POWERBLAST CANADA**

379 rue de l'Aigle, Saint-Eustache, Quebec, Canada, J7R 0M9 1-866-975-1133 www.powerblastcanada.com


TECHNICAL INFORMATION		
Solid Colors	2 colors Light Gray, Steel Gray	
Cure Time @ 21°c Recoat Traffic Full cure	12-24 hours 48 hours 7 days	
Mix Ratio (by volume)	2 component kit (by volume) 5 Part A (resin) 1 Part B (hardener)	
Coverage	25-30 wet film thickness (64-50 sqft/gal)	
Pot Life @ 25°c	30-40 minutes	
Shelf life	12 months	
Toxicity	Non-toxic Low odor No ventilation required	

PHYSICAL PROPERTY	TEST METHOD	RESULT
Adhesion to concrete CS17 / 1000 Cycles / 1000g	ASTM D-4060	6mg loss
Bond Strength	ASTM D-4541	> 300 psi (substrate failure)
Elongation (%)	ASTM D-412	444
Hardness (Shore A)	ASTM D-2240	78-80
Tensile Strength	ASTM D-638	10 mpa
Water Absorption	ASTM D-570	0.30%

- Pot life is shorter at higher temperature.
- Before using any URECO product, be sure the Safety Data Sheet (SDS) is read and understood.


LIKE & FOLLOW US ON SOCIAL MEDIA!







Linkedin/powerblastcanada





# BEYOND FLOORS...

# **URECO MEP**

# HYBRID WATERPROOFING MEMBRANE

TDSMEPEN.V01

#### SURFACE PREPARATION

Surface preparation is required. Substrate must be profiled, dry, clean, oil free, and sound. Use Ureco Degreaser to remove all contaminants (oils, greases and others). Remove any dust, laitance, dirt, curing agent impregnations, wax, foreign matter, coatings and others from the surface by an appropriate mechanical to achieve a profile equivalent to ICRI CSP 3 with Blastrac and/or diamond grinder with dust free collector. Need proper bonding to the substrate. Call the Technical Department for preparation recommendation.

#### **PRIMING**

Self-priming

#### MIXING

Pre-mix each component separately. Mix full unit. component B (hardener) into component A (resin) (mixing ratio 5 for 1 by volume) into an appropriate mixing container. Mix the combined components for at least 3 minutes using a low-speed drill (300-450 rpm) to minimize entrapping air in the system. When completely mixed, the product should be uniform in color and consistency.

## **APPLICATION**

URECO MEP is applied at 25-30 mils wet film thickness on the substrate and applied with notched squeegee and then back roll with a 10mm lint free or microfiber roller to obtain a uniform coating. Two (2) coats is recommended in access ramp with aluminum oxide mesh 24. For a complete system and maximum protection over the years, the application of a topcoat Ureco GTC is required at 15-18 mils.

NOTE: Do not exceed 24 hours between coats. If this time is exceeded, sanding of the surface is required to ensure bonding.

## **CLEANING**

This product is considered to be a low maintenance flooring solution; however, certain textures and service environments do require Please refer to the "Maintenance certain procedures. Recommendation".

#### STORAGE CONDITIONS

URECO MEP must be stored in a dry cool place between 15°C and 21ºC. Do not allow to freeze. The shelf life of this product is 12 months from ship date in the original unopened container. Do not store near open flame.

## **CHEMICAL RESISTANCE**

This product is resistant to many common chemicals. Please call the Technical Department for actual resistance to specific chemical/agents.

# MOISTURE CONCERNS

Moisture vapor transmission in the slab should be measured prior to application of polymeric systems to ensure a long lasting, durable installation.

#### **LIMITATIONS**

This product is best suited for application in temperatures between 15°C and 25°C. Substrate must be clean, sound and dry. Substrate temperature must be 3°C (5.5F) above measured dew point. Moisture content of the substrate must less than 4% when coating is applied. Do not apply to surfaces where moisture vapor can condense and freeze or to porous surfaces where moisture vapor transmission will occur during the application. Do not apply in areas where the humidity is greater than 85%. Freshly applied material should be protected from dampness, condensation and water for at least 24 hours. Compressive of the concrete should be at least 25 mpa (3625) psi at 28 days. If you have any questions, please contact the PowerBlast Canada Technical Services at 1-866-975-1133.

# **CAUTION**

Workers should wear protective clothing consisting of splash-proof goggles, impermeable gloves and, where exposure limits are exceeded, organic vapor respirators. Follow the Safety Data Sheet (SDS) for proper personal protective equipment to use when handling this product. Use only as directed.

KEEP OUT OF REACH OF CHILDREN.

IMPORTANT NOTICE- All statements, recommendations and technical information contained in this document are based on tests and information, which PowerBlast Canada believes to be accurate as of this date. The buyer should test this product before use. PowerBlast Canada assumes no obligation or liability for results obtained from the use of this product. The product and information herein are furnished at the buyers request and risk. PowerBlast Canada will not be liable for any direct, indirect, consequential, economic or any other damage whatsoever except to replace the product and or refund the purchase price to the purchaser.

# **POWERBLAST CANADA**

379 rue de l'Aigle, Saint-Eustache, Quebec, Canada, J7R 0M9 1-866-975-1133 www.powerblastcanada.com

LIKE & FOLLOW US ON SOCIAL MEDIA!







